

# technical specifications

<b>Product Name</b>	Academy
<b>Product Description</b>	Heavy Contract Carpet Tiles
<b>Pile Yarn Description</b>	85% Polypropylene 15% Nylon
<b>Tile Dimensions</b>	50cm x 50cm
<b>Pile Weight</b>	975g/m <sup>2</sup> +/-10%
<b>Total Weight</b>	4200g/m <sup>2</sup> +/-10%
<b>Total Thickness</b>	7.8mm +/-10%
<b>Backing Description</b>	Bitumen composite, 70% recycled
<b>Flammability</b>	Euroclass Bfl-s1
<b>Castor Chair Rating</b>	BS EN 985 Pass - suitable for continuous use
<b>Static Loading</b>	BS 4939:1987 (2003) Recovery >80% (24hrs)
<b>Dynamic Loading</b>	BS ISO 2094:1999 (2005) Loss <20% (1000 impacts)
<b>Body Voltage Test</b>	BS ISO 6356:2000 <2kV
<b>Colour Fastness To Light</b>	BS EN ISO 105 - B02 Minimum grade 6
<b>Colour Fastness To Shampoo</b>	BS 1006:UK-TB: 1990 Minimum grade 4
<b>Number of Tiles per Box</b>	20
<b>BREEAM RATING</b>	For specific ratings, please refer to <a href="http://www.bre.co.uk">www.bre.co.uk</a>



<b>Product Name</b>	4400 Broadway
<b>Product Description</b>	Heavy Contract Carpet
<b>Pile Yarn Description</b>	85% Polypropylene 15% Nylon
<b>Roll Length</b>	30m
<b>Roll Width</b>	2m
<b>Total Weight</b>	975g/m <sup>2</sup> +/-10%
<b>Total Thickness</b>	6.5mm +/-10%
<b>Flammability</b>	Euroclass Efl-s1*
<b>Castor Chair Rating</b>	BS EN 985 Pass - suitable for continuous use
<b>Static Loading</b>	BS 4939:1987 (2003) Recovery >80% (24hrs)
<b>Dynamic Loading</b>	BS ISO 2094:1999 (2005) Loss <20% (1000 impacts)
<b>Body Voltage Test</b>	BS ISO 6356:2000 <2kV
<b>Colour Fastness To Light</b>	BS EN ISO 105 - B02 Minimum grade 6
<b>Colour Fastness To Shampoo</b>	BS 1006:UK-TB: 1990 Minimum grade 4
<b>Sound Absorption Coefficient</b>	BS EN 354:2003
<b>Reduction in Impact Noise</b>	BS EN 140-8: Part 8: 1998 19dB
<b>BREEAM RATING</b>	For specific ratings, please refer to <a href="http://www.bre.co.uk">www.bre.co.uk</a>

\*200m2 minimum order quantity for Cfl-s1 rating



Burmatex Ltd,  
Victoria Mills, The Green,  
Ossett, West Yorkshire  
WF5 OAN, United Kingdom

Burmatex reserve the right to improve the specification of all products without prior notification. E&OE

T +44 (0) 1924 262 525  
F +44 (0) 1924 280 033  
UK email: [projects@burmatex.co.uk](mailto:projects@burmatex.co.uk)  
International email: [international@burmatex.co.uk](mailto:international@burmatex.co.uk)  
[www.burmatex.co.uk](http://www.burmatex.co.uk)